

# NYTEX SOFT

## TEST CENTER TEST REPORT

ITEM	METHOD	SPEC.
Weight (g/m <sup>2</sup> )	BSF 100	300 +/-20
Width (cm)	BS 6F 100	142,3
Tensile strength (N/5cm)	BS 6F 100	1200 1300
Tongue Tear strength (N)	BS3424 PART5 METHOD 7B	110 100
Ply-Adhesion (N/5cm)	BS 6F 100	100
Resistance to water penetration (mmH <sub>2</sub> O)	JIS L 1092 Hydrostatic	15000 ↑
Resistance to low temp.	BS 3424: PART 8 Method 10 B	No cracking -30
Air Porosity (1kg/cm <sup>2</sup> /5min)	BS 6F 100	None